


Tensar RE500 series geogrids Product specifications design temperature 15°C

Tensar RE500 geogrids are used for the reinforcement of soils in the construction of structures such as retaining walls, load bearing bridge abutments, steep slopes, slip repairs and TensarTech®Stratum® mattresses.



Properties	Units	Tensar RE500 geogrids (1), (2), (3), (4)					
		RE510	RE520	RE540	RE560	RE570	RE580
Polymer		High density polyethylene					
Minimum carbon black (5)	%	2	2	2	2	2	2
Roll width	m	1.3	1.3	1.3	1.3	1.3	1.3
Roll length	m	75	75	50	50	50	50
Unit weight	kg/m ²	0.29	0.36	0.45	0.63	0.87	0.98
Roll weight	kg	30.0	37.0	31.0	45.0	59.0	67.0
Junction strength (6)	%	95	95	95	95	95	95
Long term strength 15°C (7)							
ULS T _{CR} for 120 years (8)	kN/m	19.84	26.19	32.00	44.01	58.74	68.12
SLS T _{CS} for 1 month to 120 yrs (9)	kN/m	8.61	11.37	13.89	19.10	25.50	29.57
Quality control strength (10)							
T _{ult} (10)	kN/m	42.2	52.8	64.5	88.7	118.5	137.3
Typical load at 2% strain (10)	kN/m	9.5	12.7	16.1	23.7	26.9	38.0
Typical load at 5% strain (10)	kN/m	19.0	24.7	30.9	45.2	52.7	75.5
Typical strain at T _{ult} (10)	%	11.0	11.0	11.0	11.0	11.0	11.0

- Tensar RE500 geogrids** are stiff monolithic geogrids with integral junctions and are manufactured in accordance with Quality and Environmental Management Systems which comply with the requirements of BS EN ISO 9001:2015 and BS EN ISO 14001:2015 respectively.
- All quoted dimensions and values are typical unless stated otherwise.
- Tensar RE500 geogrids** accreditation includes:
 - The British Board of Agrément (BBA) has awarded HAPAS Certificates: No 13/H201 and No 13/H202
 - The Geotechnical Engineering Office of the Civil Engineering & Development Department of the Government of Hong Kong SAR has awarded Certificate RF 2/2017
- Tensar RE500 geogrids** are inert to all chemicals naturally found in soils and have no solvents at ambient temperature. They are not susceptible to hydrolysis and are resistant to aqueous solutions of salts, acids and alkalis (pH 2.0 to 12.5) and are non-biodegradable.
- Carbon black inhibits attack by UV light. Determined in accordance with ASTM D1603-14. Any section of grid fully exposed to sunlight can be expected to retain 90% of its quality control strength for periods in excess of 40 years in temperature climates and 20 years in tropical climates.
- Determined in accordance with GRI Test Method GG2-87, and expressed as a % of the quality control strength.
- In-soil temperature.
- ULS determined as a lower bound using standard extrapolation techniques to creep rupture data (real time test duration > 100,000 hours) obtained following the test procedure in BS EN ISO 13431:1999 for 120 year design life.
- SLS determined as the lower bound load which limits post-construction strain to 1% over the period from 1 month until design life, based on isochronous curves derived from creep tests carried out to BS EN ISO 13431:1999.
- Determined in accordance with BS EN ISO 10319:2015 and as a lower 95% confidence limit in accordance with ISO 602:1980 (BS 2846:Part 2:1981) unless otherwise stated. Strain measured via cross head travel.



The information in this document supersedes any and all prior specifications for the product(s) designated above, is of an illustrative nature and supplied by Tensar International Limited free of charge for general information purposes only. Tensar reserves the right to amend product descriptions, properties and specifications at any time and without prior notice. This document does not form part of any contract or intended contract. Tensar International Limited excludes to the fullest extent lawfully permitted any and all liability whatsoever for any loss or damage howsoever arising out of the use of and reliance upon this information. It is your sole responsibility and you must assume all risk and liability for the final determination as to the suitability of any Tensar International Limited product and/or design for the use and in the manner contemplated by you in connection with a particular project

Tensar, Tensartech and TriAx are registered trademarks

Copyright © Tensar International Limited 2019

Tensar International Limited
Tel: +44 (0) 1254 262431
Fax: +44 (0) 1254 266867
E-mail: sales@tensar.co.uk
www.tensar-international.com

UK Head Office
Units 2 - 4 Cunningham Court
Shadsworth Business Park
Blackburn
BB1 2QX
United Kingdom

