

## Rapid Repair™ GG100 Pavement Patch Solution

Specification Sheet - Rapid Repair™ GG100 Pavement Patch Solution

Specifications for Use			
Property	Test Method	Metric	Imperial
<b>Tensile Strength</b> (Ultimate) (MD x XD)*	ASTM D4595	100 x 100 kN/m	570 x 570 lbs/in.
Tensile Elongation (Ultimate)*	ASTM D4595	3%	3%
Mass/Unit Area	ASTM D5261-92	1450 g/m <sup>2</sup>	51 oz/yd²
Melting Point Bitumen Layer	ASTM C338	>93° C	>199° F
Standard Roll Length		20 m	66 ft
Standard Roll Width		1.2 m	4 ft
<b>Grid Size</b> (Center to Center of Strand)		25 x 25 mm	1.0 x 1.0 in.
Material	Fiberglass reinforcement with modified polymer coating and adhered to a polymer modified bitumen adhesive layer		

The values and tolerances given are obtained in our laboratories and in accredited testing institutions. All imperial values are approximate. The information given in this data sheet is to the best of our knowledge true and correct. However new research and practical experience can make revisions necessary. We reserve the right to make changes at any time. Statements concerning possible use of our product are not intended as recommendations for their use in the infringement of any patent. No patent warranty of any kind, expressed or implied, is made or intended.



Tensar International Corporation 2500 Northwinds Parkway Suite 500 Alpharetta, GA 30009 TensarCorp.com 800-TENSAR-1 Rapid Repair<sup>™</sup> is distributed in the United States of America, Canada and certain other countries by Tensar International Corporation (Tensar). Inasmuch as Saint-Gobain ADFORS and Tensar have no control over installation design, installation workmanship, accessory materials, or conditions of application, Saint-Gobain ADFORS and Tensar do not warrant the performance or results of any installation or use of Rapid Repair<sup>™</sup>. This warranty disclaimer includes all implied warranties, statutory or otherwise, including the warranty of merchantability and of fitness for a particular purpose.

©2016, Tensar International Corporation

<sup>\*</sup>Testing performed on the grid only.